



Values in mm / nominal

Magnetical Characteristics							@25°C
Magnet available for this series	—	1	2	3	4	5	
Type	—	NdFeB	Ferrite	—	—	—	
Grade	W/VA	N35H	Y35	—	—	—	
Remanence Br	mT	1170-1220	400-420	—	—	—	
Coercivity HcB	kA/m	>868	167-199	—	—	—	
Coercivity HcJ	kA/m	>1353	167	—	—	—	
Energy Product (BH)	kJ/m ³	263-287	30.3-31.9	—	—	—	
Environmental Characteristics							
Operating temperature	°C	-20...+85	-20...+85	—	—	—	
Material Information							
Housing material	—	Brass	Brass	—	—	—	
Housing plating	—	Ni	Ni	—	—	—	
Available Sensor		Customized version (available upon request)			Approvals		
MMS-304		Magnet type / Magnet grade			RoHS, REACH		